

DECOCORK PAINT
DATASHEET

PRODUCT CHARACTERISTICS	
Density (UNE-EN ISO 2811-1)	1,25 g/cm ³
Non-volatile matter (1h to 125°) (UNE-EN ISO 3251)	52,00 %
Non-volatile matter by volume (UNE-EN ISO 3233-3)	40,20 %
Drying time (UNE 48301) (dry film thickness: 95 µm)	Secado al tacto: 30 min. Secado total: 1h. 35 min.
Theoretical performance (R)	0,25 kg/m ² → 80 µm 0,31 kg/m ² → 100 µm
Theoretical performance (R)	5,0 m ² /l → 80 µm 4,0 m ² /l → 100 µm
pH	9±0,5



DECOPROYEC[®]

DECOPROYEC SUBERTRES, S.L. POLÍGONO INDUSTRIAL LOS MOLINOS C/Trilladores nº47, NAVE 4 y 5 - CHINCHILLA DE MONTE ARAGÓN (Albacete) C.P.: 02520
 CIF: B-02526978 · Tel.967 26 17 87 · Móvil 645 592 114 · www.decoprojec.com